

Honeywell PMP R2000

Polymethylpentene

Honeywell

Message:

The Honeywell R-Series PMP film is made from polymethylpentene. It provides more toughness and heat resistance than standard polyolefins for release film applications. R-Series Film is available in the following colors: Blue and Clear.

General Information			
Features	Heat resistance, medium		
	Good toughness		
Uses	release film		
Appearance	Blue		
	Clear/transparent		
Forms	Films		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.908	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Coefficient of Friction			ASTM D1894
With Metal-Dynamic	0.60		ASTM D1894
With self-dynamics	1.0		ASTM D1894
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
MD	600	MPa	ASTM D882
TD	662	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Yield	46.2	MPa	ASTM D882
TD: Fracture	30.3	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	180	%	ASTM D882
TD: Fracture	440	%	ASTM D882
Water Vapor Transmission	47	g/m ² /24 hr	ASTM E96
Additional Information			

Yield: 15256 in²/lbTensile Strength @ Yield, ASTM D 882, MD: 5700 to 7700 psiTensile Strength @ Break, ASTM D 882, TD: 3100 to 5700 psiElongation @ Break, ASTM 882, MD: 150 to 210%Elongation @ Break, ASTM 882, TD: 380 to 500%Secant Modulus, ASTM D 882, MD: 80000 to 94000 psiSecant Modulus, ASTM D 882, TD: 90000 to 102000 psiGraves Tear (initial), ASTM D 1004, MD: 220 to 280 g/milGraves Tear (initial), ASTM D 1004, TD: 220 to 280 g/milDimensional Stability, ASTM D1204, TD, 300°F, 10 min: <2% shrinkageDimensional Stability, ASTM D1204, MD, 300°F, 10 min: <1.5% shrinkageCoef of Friction, ASTM D1894, Vs Metal - Dynamic: 0.5 to 0.7Coef of Friction, ASTM D1894, Vs Itself - Dynamic: 0.8 to 1.2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT