Fainplast PVC KL 96

Polyvinyl Chloride

Fainplast Compounds S.r.l

Message:

Fainplast PVC KL 96 is a Polyvinyl Chloride product. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America. Typical application: Wire & Cable.

| General Information | | | |
|---------------------------|---------------------------|---------|---------------|
| Uses | Insulation | | |
| | Wire & Cable Applications | | |
| | | | |
| Wire Types | VW-1 | | |
| Agency Ratings | UL 1581, Class 43 | | |
| Physical | Nominal Value | Unit | Test Method |
| Density | 1.34 to 1.38 | g/cm³ | ISO 1183 |
| Hardness | Nominal Value | Unit | Test Method |
| Shore Hardness (Shore A) | 94 to 98 | | ISO 868 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Stress (Break) | > 19.0 | МРа | ISO 527-2 |
| Tensile Strain (Break) | > 260 | % | ISO 527-2 |
| Thermal | Nominal Value | Unit | Test Method |
| Thermal Stability | > 3 | hr | CEI 20-34/3-2 |
| Electrical | Nominal Value | Unit | Test Method |
| Volume Resistivity (23°C) | 1.0E+15 | ohms·cm | ASTM D257 |
| Flammability | Nominal Value | Unit | Test Method |
| Oxygen Index | 26 to 28 | % | ISO 4589-2 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

