

LNP*STAT-KON*DEP23FXC compound

Polycarbonate
SABIC Innovative Plastics

Message:

LNP STAT-KON* DEP23FXC is a compound based on Polycarbonate resin containing Silicone, Carbon Fiber, PTFE. Added features of this material include: Electrically Conductive.

Also known as: LNP* STAT-KON* Compound DCL-4523 SM HP

Product reorder name: DEP23FXC

General Information			
Filler / Reinforcement	Carbon Fiber		
Additive	PTFE + Silicone Lubricant		
Features	Electrically Conductive		
	Lubricated		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.29	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow : 24 hr	0.20	%	ASTM D955
Across Flow : 24 hr	0.30	%	ASTM D955
Across Flow : 24 hr	0.27	%	ISO 294-4
Flow : 24 hr	0.16	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.12	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	10500	MPa	ASTM D638
--	10200	MPa	ISO 527-2/1
Tensile Strength			
Break	121	MPa	ASTM D638
Break	123	MPa	ISO 527-2
Tensile Elongation			
Break	2.0	%	ASTM D638
Break	1.8	%	ISO 527-2
Flexural Modulus			
--	9100	MPa	ASTM D790
--	10300	MPa	ISO 178
Flexural Strength			
--	187	MPa	ASTM D790
--	186	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Notched Izod Impact			
23°C	64	J/m	ASTM D256
23°C ²	7.2	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	410	J/m	ASTM D4812
23°C ³	27	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	16.1	J	ASTM D3763
--	3.19	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	141	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	141	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	138	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	137	°C	ISO 75-2/Af
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	3.7E-5	cm/cm/°C	
Transverse : -40 to 40°C	3.3E-5	cm/cm/°C	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	10 to 1.0E+6	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, Testing by SABIC)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		
5.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT