

TAIRILAC AG12A1

Acrylonitrile Butadiene Styrene
Formosa Plastics Corporation

Message:

FCFC ABS resin AG12A1 meets the requirements of UL, SGS and the certificates of environmental protection.

General Information			
UL YellowCard	E162823-224714		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
UL File Number	E162823		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
23°C	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238, ISO 1133
200°C/5.0 kg	1.6	g/10 min	ASTM D1238, ISO 1133
220°C/10.0 kg	17	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage - Flow	0.40 - 0.70	%	Internal method
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
Class R, 23°C	105		ASTM D785
R scale, 23°C	105		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	50.0	MPa	ASTM D638, ISO 527-2
Flexural Modulus (23°C)	2450	MPa	ASTM D790, ISO 178
Flexural Strength			
23°C	73.5	MPa	ASTM D790
23°C	74.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact (23°C, 6.35 mm)	290	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648, ISO 75-2/A
1.8 MPa, unannealed, 12.7mm	84.0	°C	ASTM D648, ISO 75-2/A
1.8 MPa, annealed ¹	94.0	°C	ASTM D648, ISO 75-2/A
Vicat Softening Temperature	103	°C	ISO 306/A, ASTM D1525 ²
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm, All Colors)	HB	UL 94	

Injection	Nominal Value	Unit
Drying Temperature	70.0 - 80.0	°C
Drying Time	2.0 - 3.0	hr
Mold Temperature	40.0 - 80.0	°C
Injection Pressure	68.6 - 108	MPa
Injection instructions		
Screw Temp: 190-230°C		
NOTE		
1.	80°Cx8Hr	
2.	压力1 (10N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

