

Delrin® 911DP NC010

ACETAL RESIN

DuPont Performance Polymers

Message:

Nucleated Low Viscosity Acetal Homopolymer

General Information			
UL YellowCard	E41938-257619		
Additive	Lubricant		
	Mold Release		
Features	Lubricated		
Forms	Pellets		
Processing Method	Injection Molding		
Part Marking Code (ISO 11469)	>POM<		
Resin ID (ISO 1043)	POM		
Physical	Nominal Value	Unit	Test Method
Density	1.42	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	24	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	21.0	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.8	%	
Flow	1.9	%	
Water Absorption			ISO 62
23°C, 24 hr, 2.00 mm	0.90	%	
Equilibrium, 23°C, 2.00 mm, 50% RH	0.20	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3400	MPa	ISO 527-2
Tensile Stress (Yield)	75.0	MPa	ISO 527-2
Tensile Strain (Yield)	10	%	ISO 527-2
Nominal Tensile Strain at Break	20	%	ISO 527-2
Flexural Modulus	3300	MPa	ISO 178
Flexural Stress (3.5% Strain)	90.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	6.0	kJ/m ²	
23°C	6.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	150	kJ/m ²	

23°C	160	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	163	°C	ISO 75-2/B
1.8 MPa, Unannealed	108	°C	ISO 75-2/A
Melting Temperature ¹	178	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	1.0E-4	cm/cm/°C	
Transverse	1.0E-4	cm/cm/°C	
NOTE			
1.	10°C/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT