

# Elastollan® S98AN

Thermoplastic Polyurethane Elastomer (Polyester)

BASF Corp. Thermoplastic Polyurethanes

## Message:

Elastollan® S98AN is specifically formulated for injection molding applications with short cycling time. It exhibits good hydrolytic stability, excellent abrasion resistance, toughness, good heat, oil, fuel, and solvent resistance. It has excellent damping characteristics and outstanding resistance to tear propagation. Elastollan® S98AN is supplied uncolored in diced form.

General Information			
Features	Good Abrasion Resistance		
	Good Tear Strength		
	Good Toughness		
	High Heat Resistance		
	Hydrolytically Stable		
	Solvent Resistant		
Appearance	Colorless		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm <sup>3</sup>	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (Injection Molded)	131	MPa	ASTM D412
Flexural Modulus (Injection Molded)	138	MPa	ASTM D790
Taber Abrasion Resistance	50.0	mg	ASTM D1044
Abrasion - DIN	35	mm <sup>3</sup>	DIN 53516
Softening Point - DMA	133	°C	Internal Method
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	21.4	MPa	
300% Strain	40.7	MPa	
Tensile Strength	46.9	MPa	ASTM D412
Tensile Elongation (Break)	420	%	ASTM D412
Tear Strength <sup>1</sup>	210	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	30	%	
70°C, 22 hr	45	%	
Thermal	Nominal Value	Unit	Test Method

Glass Transition Temperature	-14.0	°C	Internal Method
Vicat Softening Temperature	157	°C	ASTM D1525
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	2.0 to 3.0	hr	
Suggested Max Moisture	0.030	%	
Rear Temperature	210 to 230	°C	
Middle Temperature	210 to 230	°C	
Front Temperature	210 to 230	°C	
Nozzle Temperature	220 to 240	°C	
NOTE			

1. Die C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

