

4LEX® 9F22105

Polycarbonate
4Plas

Message:

4LEX 9F22105 is a Standard Flow 05% Glass Fibre Reinforced Polycarbonate

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 5.0% filler by weight		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.22	g/cm ³	ISO 1183
Molding Shrinkage			
Vertical flow direction	0.50	%	
Flow direction	0.50	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 1000	ppm	ISO 960
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3500	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	75.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	8.0	kJ/m ²	ISO 180/1A
23°C	10	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	145	°C	ISO 75-2/B
1.8 MPa, not annealed	135	°C	ISO 75-2/A
Vicat Softening Temperature	148	°C	ISO 306/B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	3.0 - 4.0	hr	
Suggested Max Moisture	0.020	%	

Processing (Melt) Temp	270 - 310	°C
Mold Temperature	80.0 - 120	°C
Injection Rate	Moderate-Fast	
Holding Pressure	60.0 - 120	MPa
Screw Speed	200	rpm

Injection instructions

Feed Throat Temperature: 60 - 80 °CBack Pressure: Low

NOTE

1. 24 Hrs

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT