GATONE™ 5600X

Polyetheretherketone

Solvay Specialities India Private Limited (SSIPL)

Message:

 $\mathsf{GATONE}^{\scriptscriptstyle\mathsf{TM}}\ 5600X\ is\ a\ \mathsf{Polyetheretherketone}\ (\mathsf{PEEK})\ \mathsf{material}.\ \mathsf{It}\ is\ \mathsf{available}\ \mathsf{in}\ \mathsf{Asia}\ \mathsf{Pacific},\ \mathsf{Europe},\ \mathsf{or}\ \mathsf{North}\ \mathsf{America}.$

Important attributes of GATONE™ 5600X are:

Chemical Resistant

Heat Resistant

Radiation (Gamma) Resistant

Wear Resistant

Typical applications include:

Aerospace

Engineering/Industrial Parts

Electrical/Electronic Applications

Plumbing/Piping/Potable Water

Printing Applications

General Information					
Features	Good Chemical Resistance				
	Good Thermal Stability Good Wear Resistance				
	Machinable				
	Radiation (Gamma) Resistant				
	Tracking Resistant				
	Uses	Aerospace Applications			
Aircraft Applications					
Electrical/Electronic Applications					
Fluid Handling					
Printer Parts					
Pump Parts					
Rotating Equipment					
Valves/Valve Parts					
Forms	Pellets				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	1.30	g/cm³	ASTM D792		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Modulus	4140	МРа	ASTM D638		
Tensile Strength	90.3	МРа	ASTM D638		
Tensile Elongation (Break)	3.1	%	ASTM D638		
Flexural Modulus	3450	MPa	ASTM D790		
Flexural Strength	150	MPa	ASTM D790		

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	36	J/m	ASTM D256
Unnotched Izod Impact	No Break		ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533 Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

