

Chemlon® E-6 GF50

Polyamide 6

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® E-6 GF50 is an economy range 50% glass fibre reinforced Nylon 6 compound.
It is available in natural or black versions.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 50% filler by weight		
Appearance	Black		
	Natural color		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.56	g/cm ³	ISO 1183
Molding Shrinkage ¹	0.40 - 0.70	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	1.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	14000	MPa	ISO 527-2
Tensile Stress (Break)	220	MPa	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	13500	MPa	ISO 178
Flexural Stress ²	300	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	12	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	> 200	°C	ISO 75-2/B
1.8 MPa, not annealed	> 200	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	2.0	hr	
Rear Temperature	280 - 295	°C	
Middle Temperature	280 - 295	°C	
Front Temperature	280 - 295	°C	
Processing (Melt) Temp	< 300	°C	
Mold Temperature	80.0 - 90.0	°C	
Injection Rate	Fast		
Screw Speed	50 - 200	rpm	
Injection instructions			

Back pressure: LowInjection pressure: HighThe material is supplied dry and ready to mould in sealed, moisture proof sacks. No drying is necessary unless the material has been exposed to air for longer than three hours. The appearance of splash marks on the surface of mouldings indicates excessive moisture is present. Should drying become necessary, two hours at 80°C in a dehumidifying drier is recommended. The use of air circulating driers is not generally recommended, as longer drying times are often required, with greater potential for product oxidation and yellowing. Drying temperatures should not exceed 80°C.

NOTE	
1.	Mould shrinkage is significantly influenced by many factors including wall thickness, gating, component shape and moulding conditions.The range values stated were determined from specimen bar mouldings of 1.5mm to 4mm wall thickness. They are provided as a guide for comparison purposes only and no guarantee should be inferred from their inclusion. (Specimens measured in the dry state, 24 hours after moulding).
2.	At Break

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT