

LNP™ LUBRICOMP™ DFL36XXJ compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP* LUBRICOMP* DFL36XXJ is a compound based on Polycarbonate resin containing 30% Glass Fiber, 15% PTFE. Added features of this material include: Wear Resistant, Low Extractable, Healthcare.

Also known as: LNP* LUBRICOMP* Compound DFL-4036 HC LE

Product reorder name: DFL36XXJ

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	PTFE Lubricant (15%)		
Features	Good Wear Resistance		
	Low Extractables		
	Lubricated		
Uses	Medical/Healthcare Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.55	g/cm ³	ISO 1183, ASTM D792
Molding Shrinkage			
Flow : 24 hr	0.10 to 0.30	%	ASTM D955
Across Flow : 24 hr	0.60 to 0.80	%	ASTM D955
Across Flow : 24 hr	0.71	%	ISO 294-4
Flow : 24 hr	0.21	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	9650	MPa	ASTM D638
--	9280	MPa	ISO 527-2/1
Tensile Strength			
Yield	114	MPa	ASTM D638, ISO 527-2
Break	112	MPa	ASTM D638
Break	113	MPa	ISO 527-2
Tensile Elongation			
Yield	2.4	%	ASTM D638
Yield	2.5	%	ISO 527-2
Break	2.5	%	ASTM D638
Break	2.7	%	ISO 527-2
Flexural Modulus			
--	8960	MPa	ASTM D790
--	8700	MPa	ISO 178

Flexural Strength			
--	179	MPa	ASTM D790
--	180	MPa	ISO 178
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.58		
vs. Itself - Static	0.50		
Wear Factor - Washer	27.5	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	180	J/m	ASTM D256
23°C ²	17	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	850	J/m	ASTM D4812
23°C ³	52	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	21.8	J	ASTM D3763
--	7.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	147	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ⁴	149	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	143	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁵	144	°C	ISO 75-2/Af
CLTE			
Flow : -40 to 40°C	4.7E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Transverse : -40 to 40°C	3.1E-5	cm/cm/°C	ASTM E831
Transverse : -40 to 40°C	3.0E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 to 304	°C	
Middle Temperature	310 to 321	°C	
Front Temperature	321 to 332	°C	
Processing (Melt) Temp	304 to 327	°C	
Mold Temperature	82.2 to 110	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		

4.	80*10*4 mm
5.	80*10*4 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

