

Nypol® PA A3 G30 CNZ0342 NR433

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 in color gray reinforced with 30% of fiberglass, good set of thermal and mechanical properties. Ideal for injection molding.

General Information				
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Appearance		Grey		
Processing Method		Injection Molding		
Resin ID (ISO 1043)		>PA 66 GF30<		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity	1.36 to 1.38	--	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30	--	%	ASTM D955
Water Absorption				ASTM D570
Saturation	6.0	--	%	
Equilibrium	1.9	--	%	
Ash Content	28 to 32	--	%	ASTM D2584
Relative Viscosity - Formic Acid	46.0 to 52.0	--		
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	9700	7000	MPa	ASTM D638
Tensile Strength	200	135	MPa	ASTM D638
Tensile Elongation (Break)	3.2	5.0	%	ASTM D638
Flexural Modulus	12200	6500	MPa	ASTM D790
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12	16	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength				ISO 179
-30°C	--	70	kJ/m ²	
23°C	> 70	> 70	kJ/m ²	
Notched Izod Impact (Area) (23°C)	11.0	14.0	kJ/m ²	ASTM D256
Unnotched Izod Impact (Area)				ASTM D256
-30°C	--	70.0	kJ/m ²	
23°C	> 70.0	> 70.0	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ASTM D648

0.45 MPa, Unannealed	260	--	°C	
1.8 MPa, Unannealed	250	--	°C	
Melting Temperature	250 to 265	--	°C	ASTM D2117
Flammability	Dry	Conditioned		Test Method
Flame Rating	HB	--		UL 94
Injection	Dry	Unit		
Drying Temperature	90.0		°C	
Drying Time	4.0		hr	
Processing (Melt) Temp	270 to 285		°C	
Mold Temperature	80.0 to 90.0		°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

