

4MID® 9B22140 HUV

Polyamide 6
4Plas

Message:

4MID 9B22140 HUV is a Prime Standard Flow 40% Glass Fibre Reinforced Heat & UV Stabilised PA6

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 40% filler by weight		
Additive		heat stabilizer		
		UV stabilizer		
Features		Good UV resistance		
		Thermal Stability		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.46	--	g/cm ³	ISO 1183
Molding Shrinkage				
Vertical flow direction	0.90	--	%	
Flow direction	0.20	--	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	1.8	--	%	ISO 62
Moisture Content	< 2000	--	ppm	ISO 960
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	12500	8000	MPa	ISO 527-2/50
Tensile Stress (Break, 23°C)	160	110	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.5	--	%	ISO 527-2/5
Impact	Dry	Conditioned	Unit	Test Method
Notched Izod Impact				ISO 180/1A
-30°C	12	--	kJ/m ²	ISO 180/1A
23°C	14	--	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	70	--	kJ/m ²	ISO 180/1U
23°C	80	--	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	220	--	°C	ISO 75-2/B
1.8 MPa, not annealed	210	--	°C	ISO 75-2/A

Vicat Softening Temperature	215	--	°C	ISO 306/B
Melting Temperature ²	223	--	°C	ISO 11357
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+13	--	ohms	IEC 60093
Volume Resistivity	1.0E+15	--	ohms·cm	IEC 60093
Comparative Tracking Index	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.750 mm	HB	--		UL 94
1.60 mm	HB	--		UL 94
Glow Wire Ignition Temperature (2.00 mm)	650	--	°C	IEC 60695-2-13
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0		hr	
Suggested Max Moisture	0.20		%	
Processing (Melt) Temp	250 - 270		°C	
Mold Temperature	60.0 - 100		°C	
Injection Rate	Fast			
Holding Pressure	50.0 - 100		MPa	
Screw Speed	200		rpm	
Injection instructions				
Feed Throat Temperature: 60 - 80 °C Back Pressure: Low				
NOTE				
1.	24 Hrs			
2.	10 K/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

