

SLOVALEN® EH 96 FRD 2

Polypropylene

Plastcom

Message:

Determined for environment, where contact with water is possible, because the electric properties do not change by conditioning. Application - terminals, coil forms, guides in washing machines, tea-pots, dish-washers. Delivered in natural mode and in the full RAL colour scale. Modified homopolymer PP, retarded type with halogen flame retardant. Fulfills basic electric properties: flammability in accordance with UL 94 V2 and 850°C glow wire.

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
	Halogenated		
	Homopolymer		
Uses	Appliances		
	Electrical/Electronic Applications		
	White Goods & Small Appliances		
Appearance	Colors Available		
	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PP		
Physical	Nominal Value	Unit	Test Method
Density	1.01	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Molding Shrinkage			STM 64 0808
Across Flow	2.2	%	
Flow	2.4	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1200	MPa	ISO 527-2
Tensile Stress (Yield)	18.0	MPa	ISO 527-2
Tensile Strain (Yield)	33	%	ISO 527-2
Flexural Modulus	900	MPa	ISO 178
Flexural Stress	21.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	6.0	kJ/m ²	
23°C	10	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179

-20°C	45	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	55.0	°C	ISO 75-2/B
Vicat Softening Temperature	100	°C	ISO 306/B
Melting Temperature (DSC)	130	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength	28	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	500	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-2		UL 94
Glow Wire Ignition Temperature	850	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Processing (Melt) Temp	170 to 190	°C	
Mold Temperature	30.0 to 50.0	°C	
Injection Pressure	50.0 to 80.0	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

