

Veroplas VF790

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Veroplas VF790 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Europe or North America.

Characteristics include:

Flame Rated

Flame Retardant

General Information			
UL YellowCard	E315545-100118272		
Features	Flame Retardant		
	General Purpose		
Uses	General Purpose		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.09	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	13	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.60	%	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	38.6	MPa	ASTM D638
Flexural Modulus	2030	MPa	ASTM D790
Flexural Strength	58.6	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	180	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	91.1	°C	ASTM D648
Vicat Softening Temperature	103	°C	ASTM D1525
Flammability	Nominal Value	Test Method	
Flame Rating (1.70 mm, ALL)	V-2	UL 94	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

