

TRIPET® 2550GN40

Polyethylene Terephthalate
Samyang Corporation

Message:

TRIPET® 2550GN40 is a Polyethylene Terephthalate (PET) product. It is available in Asia Pacific, Europe, or North America. Primary characteristic: flame rated.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.72	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (265°C/5.0 kg)	70	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	< 0.10	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	117		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	142	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Flexural Modulus	9810	MPa	ASTM D790
Flexural Strength (Yield)	177	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	69	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	250	°C	
1.8 MPa, Unannealed	225	°C	
CLTE - Flow	3.0E-5	cm/cm/°C	ASTM D696
RTI Elec (3.00 mm)	140	°C	UL 746
RTI Imp (3.00 mm)	140	°C	UL 746
RTI Str (3.00 mm)	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms · cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant	3.80		ASTM D150
Dissipation Factor	0.017		ASTM D150
Arc Resistance	80.0	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.750 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

