

Hostacom D1171 9176

Polyolefin

LyondellBasell Industries

Message:

25% talc filled copolymer,antistatic. Previously known as 2611PC TA5.

General Information			
Filler / Reinforcement	Talc filler, 25% filler by weight		
Additive	Antistatic property		
Features	Copolymer		
	Antistatic property		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - Secant	2000	MPa	ISO 527-2
Tensile Stress (Yield)	21.0	MPa	ISO 527-2/50
Flexural Modulus - Secant	2100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-20°C	2.9	kJ/m ²	ISO 179
23°C	8.8	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	110	°C	ISO 75-2/B
1.8 MPa, not annealed	60.0	°C	ISO 75-2/A
Vicat Softening Temperature	55.0	°C	ISO 306
Additional Information			

Coefficient of Linear thermal Expansion, DIN 53752, 23 - 85°C, Parallel: 0.75 1/KFlammability, FMVSS 302: 40 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

