

MARPOL® Homo 65.NA

Polypropylene Homopolymer

Marco Polo International, Inc.

Message:

Additives: Nucleation and Antistat

Recommended Applications: Caps, closures, and thin wall containers

General Information	
Additive	Antistatic Nucleating Agent
Features	Antistatic Food Contact Acceptable Homopolymer Nucleated
Uses	Caps Closures Thin-walled Containers

Physical	Nominal Value	Unit	Test Method
Density	0.905	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	65	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1830	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	21	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT