

Kepital® MX20BT01

Acetal (POM) Copolymer

KEP Americas

Message:

Medium viscosity grade for medical device applications. KEPITAL MX20BT01 can be processed by general injection molding.

General Information			
Features	Low liquidity		
Uses	Medical/nursing supplies		
Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
shrinkage-Flow ¹ (3.00 mm)	2.0	%	Internal method
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	64.0	MPa	ISO 527-2/50
Tensile Strain (Yield)	9.0	%	ISO 527-2
Nominal Tensile Strain at Break	32	%	ISO 527-2
Flexural Modulus (23°C)	2550	MPa	ISO 178
Flexural Stress (23°C)	87.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	6.5	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	100	°C	ISO 75-2/A
Melting Temperature	165	°C	ISO 11357-3
CLTE - Flow	1.2E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Dielectric Strength	19	kV/mm	IEC 60243-1
NOTE			
1.	100mm diameter		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

