

Honeywell PCTFE P8000LS

Polychlorotrifluoroethylene

Honeywell

Message:

Honeywell PCTFE P-Series LS film is a poly-chlor-tri-fluoroethylene homopolymer, low shrink, high performance barrier film for industrial and electronics applications. It provides outstanding water vapor barrier and excellent chemical resistance.

General Information			
Features	Homopolymer		
	Good chemical resistance		
	Low shrinkage		
	Barrier resin		
Uses	Electrical/Electronic Applications		
	Industrial application		
Forms	Films		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	2.10	g/cm ³	ASTM D792
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
MD	1450	MPa	ASTM D882
TD	1450	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Fracture	37.9	MPa	ASTM D882
TD: Fracture	37.9	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	160	%	ASTM D882
TD: Fracture	190	%	ASTM D882
Water Vapor Transmission	0.023	g/m ² /24 hr	ASTM E96
Thermal	Nominal Value	Unit	Test Method
Peak Crystallization Temperature (DSC)	211	°C	ASTM D3418
Flammability	Nominal Value	Unit	Test Method
Oxygen Index	100	%	ASTM D2863
Optical	Nominal Value	Unit	Test Method
Haze	< 1.0	%	ASTM D1003
Additional Information			

Yield: 1633 in²/lbTensile Strength @ Break, ASTM D 882, MD: 5000 to 6000 psiTensile Strength @ Break, ASTM D 882, TD: 5000 to 6000 psiElongation @ Break, ASTM 882, MD: 110 to 200%Elongation @ Break, ASTM 882, TD: 150 to 220%Secant Modulus, ASTM D 882, MD: 190000 to 225000 psiSecant Modulus, ASTM D 882, TD: 190000 to 225000 psiGraves Tear (initial), ASTM D 1004, MD: 450 to 525 g/milGraves Tear (initial), ASTM D 1004, TD: 450 to 525 g/milDimensional Stability, ASTM D1204, TD, 300°F, 10 min: <2% shrinkageDimensional Stability, ASTM D1204, MD, 300°F, 10 min: <2% shrinkageFlammability: Non-flammable

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

