

# Kemcor LD 9150

Low Density Polyethylene

Qenos Pty Ltd

Message:

This resin is manufactured to conform to the requirements for unrestricted food contact of AS 2070 Part 1 (1980).

General Information			
Features	General Purpose		
	Good Processability		
	High Flow		
	High Gloss		
Uses	Household Goods		
	Toys		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	35	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.0 to 3.0	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	43		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	140	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	8.00	MPa	
Break	10.0	MPa	
Tensile Elongation (Break)	150	%	ASTM D638
Injection	Nominal Value	Unit	
Processing (Melt) Temp	170 to 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: [sales@su-jiao.com](mailto:sales@su-jiao.com)

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

