

Durethan® AKV 35 CX H2.0 900876

Polyamide 66

LANXESS Asia/Pacific

Message:

PA 66, 35 % glass fibers, injection molding, heat aging stabilized

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 35% filler by weight		
Features	Thermal Stability		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.41	g/cm ³	ISO 1183
Molding Shrinkage			ISO 2577
Vertical flow direction: 290°C, 2.00mm ¹	0.90	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.070	%	ISO 2577
Flow direction: 290°C, 2.00mm ³	0.30	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.070	%	ISO 2577
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	11000	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	197	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	2.8	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	10900	MPa	ISO 178/A
Flexural Stress ⁶ (23°C)	296	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	3.2	%	ISO 178/A
ISO Shortname	PA 66, GHR, 12-110, GF35		ISO 1874
Residual Moisture Content	0.020 - 0.070	%	Karl Fisher
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	58	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	> 240	°C	ISO 75-2/A
Melting Temperature ⁸	260	°C	ISO 11357-3
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Dry Air Dryer	80.0	°C	
Drying Time - Dry Air Dryer	2.0 - 6.0	hr	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	80.0 - 120	°C	
NOTE			
1.	60x60x2mm, 80°C MT, 600 bar		

2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

