

Sarlink® TPE EE-2268DN

Thermoplastic Polyolefin Elastomer

Teknor Apex Company

Message:

Sarlink EE-2268DN is a medium impact, modified polypropylene used in transportation applications. Sarlink EE-2268DN is a high hardness grade and UV resistant. This grade can be processed by extrusion or injection molding.

General Information	
Features	Sunlight Resistant
	Light stabilization
	Low liquidity
	Fill
	High hardness
	Medium density
Uses	Application in Automobile Field
	Automotive exterior parts
	Car exterior decoration
	General
RoHS Compliance	RoHS compliance
Appearance	Opacity
Forms	Particle
Processing Method	Extrusion
	Injection molding

Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness ¹			ISO 868
Shore D, 1 second, injection molding	73		ISO 868
Shore D, 5 seconds, injection molding	69		ISO 868
Shore D, 15 seconds, injection molding	68		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus	1690	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress ²			ISO 37
Transverse flow: 100% strain	14.8	MPa	ISO 37
Flow: 100% strain	14.5	MPa	ISO 37

Tensile Stress ³			ISO 37
Transverse flow: Fracture	21.8	MPa	ISO 37
Flow: Fracture	25.1	MPa	ISO 37
Tensile Elongation ⁴			ISO 37
Transverse flow: Fracture	320	%	ISO 37
Flow: Fracture	140	%	ISO 37
Tear Strength ⁵			ISO 34-1
Transverse flow	210	kN/m	ISO 34-1
Flow	140	kN/m	ISO 34-1
Compression Set ⁶			ISO 815
23°C, 22 hr	63	%	ISO 815
70°C, 22 hr	86	%	ISO 815
90°C, 70 hr	93	%	ISO 815
125°C, 70 hr	100	%	ISO 815
Aging	Nominal Value	Unit	Test Method
Change in Tensile Strength in Air ⁷			ISO 188
Transverse flow: 110°C, 1008 hr	1.8	%	ISO 188
Flow: 110°C, 1008 hr	9.0	%	ISO 188
Transverse flow: 100% strain 110°C, 1008 hr	12	%	ISO 188
Flow: 100% strain 110°C, 1008 hr	68	%	ISO 188
Transverse flow: 125°C, 168 hr	-2.8	%	ISO 188
Flow: 125°C, 168 hr	2.4	%	ISO 188
Transverse flow: 100% strain 125°C, 168 hr	15	%	ISO 188
Flow: 100% strain 125°C, 168 hr	75	%	ISO 188
Change in Tensile Strain at Break in Air ⁸			ISO 188
Transverse flow: 110°C, 1008 hr	-58	%	ISO 188
Flow: 110°C, 1008 hr	-7.2	%	ISO 188
Transverse flow: 125°C, 168 hr	-54	%	ISO 188
Flow: 125°C, 168 hr	27	%	ISO 188
Change in Shore Hardness in Air			
Support d, 110°C, 1008 hr ⁹	2.3		ISO 188
Support d, 110°C, 1008 hr ¹⁰	2.0		ISO 188
Support c, 125°C, 168 hr ¹¹	1.1		ISO 188
Support d, 125°C, 168 hr ¹²	1.3		ISO 188
Support d, 125°C, 168 hr ¹³	1.2		ISO 188
Fill Analysis	Nominal Value	Unit	Test Method
Apparent Viscosity (200°C, 206 sec ⁻¹)	560	Pa · s	ASTM D3835
Legal statement			

The information and recommendations contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchaser assumes all risks and liability for the results of use of the products, including use in accordance with seller's recommendations. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or others. There is no warranty of merchantability and there are no other warranties for the products described. For detailed Product Stewardship information, please contact us. Any product of Teknor Apex, including product names, shall not be used or tested in medical or food contact applications without the prior written acknowledgement of Teknor Apex as to the intended use. Please note that some products may not be available in one or more countries.

Injection	Nominal Value	Unit
Rear Temperature	171 - 193	°C
Middle Temperature	177 - 199	°C
Front Temperature	182 - 204	°C
Nozzle Temperature	188 - 210	°C
Processing (Melt) Temp	188 - 210	°C
Mold Temperature	25 - 66	°C
Injection Pressure	1.38 - 6.89	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.172 - 0.345	MPa
Screw Speed	50 - 100	rpm
Cushion	3.81 - 25.4	mm

Injection instructions

Drying is not necessary. However, if moisture is a problem, dry the pellets for 2 to 4 hours at 150°F (65°C).

Extrusion	Nominal Value	Unit
Cylinder Zone 1 Temp.	166 - 188	°C
Cylinder Zone 2 Temp.	171 - 193	°C
Cylinder Zone 3 Temp.	177 - 199	°C
Cylinder Zone 4 Temp.	191 - 210	°C
Cylinder Zone 5 Temp.	182 - 204	°C
Die Temperature	190 - 210	°C

Extrusion instructions

Screw Speed: 30 to 100 rpm

NOTE

- 24 hrs
- Type 1, 510mm/min
- Type 1, 510mm/min
- Type 1, 510mm/min
- B method, right angle specimen (without cut), 510mm/min
- Type a
- Type 1
- Type 1
- 15 sec
- 5 sec
- 1 sec
- 15 sec

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

