

Oleflex™ 6261-70A-8843 Black, 307105

Thermoplastic Elastomer

Vi-Chem Corporation

Message:

Oleflex™6261-70A-8843 Black, 307105 is a thermoplastic elastomer (TPE) material. This product is available in North America.

General Information			
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.09	g/cm³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shao A, mm)	70		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/5A
2.00 mm	2.60	MPa	ISO 527-2/5A
70°C, 2.00 mm ¹	2.60	MPa	ISO 527-2/5A
Tensile Strain			ISO 527-2/5A
Fracture, 2.00mm	500	%	ISO 527-2/5A
Fracture, 70°C, 2.00mm ²	470	%	ISO 527-2/5A
Wear resistance (mm) ³	5000		SAE J948
Cold flexibility-High and Low Bend Test			
-30°C, 2.54 cm	Pass		
-24°C, 2.54 cm	Pass		
Combustibility (mm)	33	mm/min	FMVSS 302
Atomization (mm) ⁴	99.0		SAE J1756
Surface Temperature - Heat Resistance (85°C, 2.00 mm) ⁵	5.00		
Xenon Arc - Delta E ⁶	0.0700		SAE J1885
Elastomers	Nominal Value	Unit	Test Method
Tear Strength (2.00 mm)	17.8	kN/m	ASTM D624
Compression Set			
70°C, 7 hr	47	%	ASTM D395
70°C, 22 hr	49	%	ASTM D395B
Additional Information	Nominal Value	Test Method	
Hot Odor Test, SAE J1351: 1.4			
NOTE			
1.	After 7 h @ 70°C		
2.	After 7 h @ 70°C		
3.	Tested according to SAE J948/ASTM D3884		
4.	Method B		

5.	168 h @ 85°C
6.	200 hours, 267 kJ/m ²

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China

