

Chemlon® 533 G

Polyamide 66

Teknor Apex Company (Chem Polymer)

Message:

Chemlon® 533 G is a Polyamide 66 (Nylon 66) material filled with 33% glass fiber. It is available in Asia Pacific, Europe, or North America for injection molding.

Important attributes of Chemlon® 533 G are:

Good Aesthetics

High Strength

Impact Resistant

Typical application of Chemlon® 533 G: Automotive

General Information			
Filler / Reinforcement	Glass Fiber,33% Filler by Weight		
Features	Good Impact Resistance		
	High Tensile Strength		
	Pleasing Surface Appearance		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	141	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	2.0	%	ASTM D638
Flexural Modulus (23°C)	6890	MPa	ASTM D790
Flexural Strength (23°C)	217	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	75	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	249	°C	ASTM D648
Melting Temperature	254	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

