

CERTENE™ 705 SAN

Styrene Acrylonitrile
Muehlstein

Message:

CERTENE™ 705 SAN is a Styrene Acrylonitrile (SAN) material. It is available in North America.

General Information			
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.07	g/cm³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	7.5	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.30 to 0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	83		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3280	MPa	ASTM D638
Tensile Strength (Break)	72.4	MPa	ASTM D638
Flexural Modulus	3450	MPa	ASTM D790
Flexural Strength (Yield)	115	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	21	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 12.7 mm)	96.1	°C	ASTM D648
Vicat Softening Temperature	106	°C	ISO 306/B50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China


WECHAT