

Nypol® PA A3 G15 HS UV RH PRTA011 NR303

Polyamide 66

Petropol Industry and Trade of Polymers LTDA

Message:

Polyamide 6.6 in black color reinforced with 15% fiberglass, thermo stable, resistance to hydrolysis and UV. Good set of thermal properties, electrical and mechanical. Ideal pair injection molding.

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Features	Good Thermal Stability		
	Good UV Resistance		
	Hydrolysis Resistant		
Appearance	Black		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	>PA 66 GF15<		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.22 to 1.23	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.60 to 0.90	%	ASTM D955
Water Absorption (24 hr)	1.3	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	117	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	4900	MPa	ASTM D790
Flexural Strength	160	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	48	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	238	°C	ASTM D648
Melting Temperature	260	°C	ASTM D2117
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Processing (Melt) Temp	260 to 280	°C	
Mold Temperature	70.0 to 100	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

