

Star T PA6 65E12

Polyamide 6
Eurostar Engineering Plastics

Message:

Star T PA6 65E12 is a Polyamide 6 Injection Molding Resin with Improved Thermal Conductivity

General Information			
Features	Heat conduction		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.99	g/cm ³	ISO 1183
shrinkage-Flow (4.00 mm)	1.0 - 1.6	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	85.0	MPa	ISO 527-2
Tensile Strain (Break)	2.5	%	ISO 527-2
Flexural Modulus	7200	MPa	ISO 178
Flexural Stress	115	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	4.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	35	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (1.8 MPa, Unannealed, 64.0 mm Span)	80.0	°C	ISO 75-2/Af
Thermal Conductivity ²	1.4	W/m/K	Internal method
Injection	Nominal Value	Unit	
Drying Temperature	80	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	250 - 260	°C	
Middle Temperature	260 - 280	°C	
Front Temperature	260 - 280	°C	
Processing (Melt) Temp	260 - 280	°C	
Mold Temperature	60 - 90	°C	
NOTE			
1.	80x10x4 mm		
2.	In-plane		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

