

Hylex® P1025 L1 HB

Polycarbonate

Entec Polymers

Message:

Hylex® P1025 L1 HB is a Polycarbonate (PC) material. It is available in North America.

Important attributes of Hylex® P1025 L1 HB are:

Flame Rated

RoHS Compliant

Typical application of Hylex® P1025 L1 HB: Food Contact Applications

General Information			
UL YellowCard	E157012-538662		
Features	General Purpose		
Uses	General Purpose		
Agency Ratings	FDA 21 CFR 177.1580		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	25	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	72		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break, 23°C)	65.5	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	120	%	ASTM D638
Flexural Modulus (23°C)	2310	MPa	ASTM D790
Flexural Strength (23°C)	93.1	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	640	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	132	°C	
1.8 MPa, Unannealed	127	°C	
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.586		ASTM D542
Transmittance	88.0	%	ASTM D1003
Haze	1.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

