

# Polyrocks 8200MP90V

Polyphenylene Ether

Polyrocks Chemical Co., Ltd

## Message:

High strength halogen-free flame retardant thermoplastic polyolefin wire & cable compound is environmental flame retardant material with phosphorus and nitrogen as flame retardant elements. Carbonize and swelling mechanism play the flame retardant performance. High strength halogen-free flame retardant polyolefin wire & cable compound, which Mechanical properties meet the UL requirements of MPPE/MPPE-PE wire and cable , flammability reach UL1581 VW-1, Matt matte, low temperature resistance, PS/ABS migration resistance, no red phosphorus, and meet the requirements of ROHS, SVHC, PFOS & PFOA, 16P, Halogen, PAHs...etc.

General Information			
Additive	Flame retardancy 2		
Features	High strength		
	Low temperature resistance		
	Halogen-free		
	Flame retardancy		
Uses	Wire and cable applications		
	Wire sheath		
	Insulating material		
Wire Types (UL 1581)	VW-1		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS compliance		
Appearance	Rough surface polishing		
Forms	Particles		
Physical	Nominal Value	Unit	
Density	1.10	g/cm <sup>3</sup>	
Hardness	Nominal Value	Unit	
Durometer Hardness (Shore A)	91		
Elastomers	Nominal Value	Unit	
Tensile Strength	23.0	MPa	
Tensile Elongation (Break)	220	%	
Aging	Nominal Value	Unit	
Change in Tensile Strength in Air (136°C, 168 hr)	5.0	%	
Change in Ultimate Elongation in Air (136°C, 168 hr)	-5.0	%	
Thermal	Nominal Value	Unit	
Brittleness Temperature	< -40.0	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (20°C)	8.3E+17	ohms · cm	

Dielectric Strength	28	kV/mm	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (6.0 mm)	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

