

# Tecodur® PB70 GB30 NL

Polybutylene Terephthalate  
Eurotec Engineering Plastics

## Message:

PBT, 30% glass bead reinforced, natural

General Information			
Filler / Reinforcement	Glass Bead,30% Filler by Weight		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PBT GB30		
Physical	Nominal Value	Unit	Test Method
Density	1.52	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	1.2	%	
Flow	1.2	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 0.080	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	4000	MPa	ISO 527-2
Tensile Stress (Break, 23°C)	60.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.5	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	3.0	kJ/m <sup>2</sup>	
23°C	4.0	kJ/m <sup>2</sup>	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	30	kJ/m <sup>2</sup>	
23°C	35	kJ/m <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	180	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	°C	ISO 75-2/A
Vicat Softening Temperature	190	°C	ISO 306/B
Melting Temperature <sup>1</sup>	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method

Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	HB		
1.60 mm	HB		
Injection	Nominal Value	Unit	
Drying Temperature	120	°C	
Drying Time	2.0 to 4.0	hr	
Hopper Temperature	50.0 to 70.0	°C	
Processing (Melt) Temp	250 to 270	°C	
Mold Temperature	60.0 to 100	°C	
Injection Rate	Fast		
Holding Pressure	40.0 to 80.0	MPa	
NOTE			
1.	10 K/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

