

SCHULADUR® A3 GF 10

Polybutylene Terephthalate + ASA

A. Schulman Europe

Message:

10% glass fibre reinforced PBT-ASA blend with high surface quality and reduced warpage

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Low warpage		
	Excellent appearance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.28	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (250°C/2.16 kg)	12.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4300	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	70.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.8	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	5.0	kJ/m ²	ISO 179/1eA
23°C	5.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	43	kJ/m ²	ISO 179/1eU
23°C	45	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	133	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	189	°C	ISO 306/A50
--	142	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flammability Classification			IEC 60695-11-10, -20
1.50 mm	HB		IEC 60695-11-10, -20
3.00 mm	HB		IEC 60695-11-10, -20
Additional Information			

- 1.)
- Not for use in food contact applications2.)
- Not for use in medical or pharmaceutical applications

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

