

NORYL GTX™ GTX987 resin

Polyphenylene Ether + PS + Nylon

SABIC Innovative Plastics

Message:

Conductive GTX, CTE 7

General Information			
Features	Conductivity		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.25	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	8.5	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	7.50	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	1.0 - 1.4	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	3.0	%	ISO 62
Equilibrium, 23°C, 50% RH	0.90	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	3250	MPa	ASTM D638
--	3000	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	55.0	MPa	ASTM D638
Yield	62.0	MPa	ISO 527-2/50
Fracture ³	55.0	MPa	ASTM D638
Fracture	62.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	5.0	%	ASTM D638
Yield	5.0	%	ISO 527-2/50
Fracture ⁵	15	%	ASTM D638
Fracture	20	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2700	MPa	ASTM D790
-- ⁷	2800	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0mm span ⁸	95.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength ⁹ (23°C)	11	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	70	J/m	ASTM D256
23°C	90	J/m	ASTM D256
-30°C ¹⁰	8.0	kJ/m ²	ISO 180/1A
23°C ¹¹	15	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	10.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	185	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹²	190	°C	ISO 75-2/Bf
Vicat Softening Temperature			
--	192	°C	ASTM D1525 ¹³
--	198	°C	ISO 306/B50
--	200	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 60°C	5.5E-5	cm/cm/°C	ASTM E831
Flow: 23 to 60°C	7.0E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 60°C	6.0E-5	cm/cm/°C	ASTM E831
Lateral: 23 to 60°C	7.5E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	100 - 110	°C	
Drying Time	2.0 - 3.0	hr	
Suggested Max Moisture	0.020	%	
Hopper Temperature	80.0 - 100	°C	
Rear Temperature	260 - 280	°C	
Middle Temperature	280 - 300	°C	
Front Temperature	300 - 320	°C	
Nozzle Temperature	280 - 300	°C	
Processing (Melt) Temp	300 - 320	°C	
Mold Temperature	100 - 120	°C	
NOTE			
1.	50 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*4 sp=62mm		

10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

