

Braskem PP C104-01

Polypropylene Impact Copolymer

Braskem America Inc.

Message:

Description

Good Stiffness

Applications

Suggested Uses Include Extrusion and Thermoforming Applications Where Impact Resistance at Refrigeration Temperatures is Desired, Especially Suited for Corrugated Board Applications

General Information	
Features	Food Contact Acceptable Good Stiffness Impact Copolymer Low Temperature Impact Resistance
Agency Ratings	FDA 21 CFR 177.1520
Forms	Pellets
Processing Method	Extrusion Thermoforming

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield)	27.0	MPa	ASTM D638
Tensile Elongation ² (Yield)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ³	1240	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	190	J/m	ASTM D256A

NOTE	
1.	50 mm/min
2.	50 mm/min
3.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

