

4PROP® 9D02420 FRC5HUV

Polypropylene Homopolymer
4Plas

Message:

4PROP 9D02420 FRC5HUV is a MFI 4 20% Chemically Coupled Glass Fibre FR Halogen Free Formulated To Meet Crib 5, Heat & UV Stabilised Homopolymer Polypropylene

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	heat stabilizer		
	UV stabilizer		
Features	Chemical coupling		
	Homopolymer		
	Good UV resistance		
	Thermal Stability		
	Halogen-free		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	5000	MPa	ISO 527-2/5
Tensile Stress (Break, 23°C)	70.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	%	ISO 527-2/5
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ISO 180/1A
-30°C	6.0	kJ/m ²	ISO 180/1A
23°C	7.0	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Melting Temperature ¹	170	°C	ISO 11357
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (1.00 mm)	850	°C	IEC 60695-2-12
Additional Information			
Ignitability - Ignition Source 5 - NI/5 (BS5852:2006)			
Injection	Nominal Value	Unit	

Processing (Melt) Temp	200 - 240	°C
Mold Temperature	20.0 - 50.0	°C
Injection Rate	Moderate	
Holding Pressure	40.0 - 80.0	MPa
Screw Speed	200	rpm

Injection instructions

Feed Throat Temperature: 20 - 60 °C Back Pressure: Low

NOTE

1. 10 K/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

