

LNP™ THERMOCOMP™ YF005 compound

Thermoplastic Polyester Elastomer

SABIC Innovative Plastics

Message:

LNP THERMOCOMP YF005 is a compound based on Polyester Elastomer resin containing 25% Glass Fiber.

Also known as: LNP* THERMOCOMP* Compound YF-1005

Product reorder name: YF005

General Information			
Filler / Reinforcement	Glass Fiber,25% Filler by Weight		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.40	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow : 24 hr	0.50 to 0.70	%	
Across Flow : 24 hr	1.0 to 3.0	%	
Water Absorption			
24 hr, 50% RH	0.31	%	ASTM D570
Equilibrium, 23°C, 50% RH	0.41	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2370	MPa	ASTM D638
--	2360	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	47.0	MPa	ASTM D638
Yield	46.0	MPa	ISO 527-2/5
Break ³	46.0	MPa	ASTM D638
Break	45.0	MPa	ISO 527-2/5
Tensile Elongation			
Yield ⁴	9.9	%	ASTM D638
Yield	9.5	%	ISO 527-2/5
Break ⁵	8.3	%	ASTM D638
Break	10	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁶	1980	MPa	ASTM D790
-- ⁷	2120	MPa	ISO 178
Flexural Stress	53.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	330	J/m	ASTM D256
23°C ⁸	29	kJ/m ²	ISO 180/1A

Unnotched Izod Impact			
23°C	1000	J/m	ASTM D4812
23°C ⁹	76	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Total Energy	15.7	J	ASTM D3763
--	7.80	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	186	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁰	180	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	152	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹¹	142	°C	ISO 75-2/Af
CLTE			ASTM D696
Flow : -30 to 30°C	3.6E-5	cm/cm/°C	
Transverse : -30 to 30°C	1.8E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.10	%	
Rear Temperature	182 to 193	°C	
Middle Temperature	204 to 216	°C	
Front Temperature	227 to 238	°C	
Processing (Melt) Temp	216 to 238	°C	
Mold Temperature	26.7 to 54.4	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	50 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	Type I, 5.0 mm/min		
5.	Type I, 5.0 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	80*10*4		
9.	80*10*4		
10.	80*10*4 mm		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

