

INSULCAST® 136/INSULCURE 11B

Epoxy; Epoxide

ITW Polymers Coatings North America

Message:

INSULCAST 136 is an easy to use epoxy casting/potting compound exhibiting excellent adhesion to metals, ceramics and most plastics. When properly cured with INSULCURE 11B, INSULCAST 136 will conform to the requirements of MIL-I-16923, Types B, C & D, and will not support fungus growth.

General Information			
Features	Fungus Resistant		
	General Purpose		
	Good Adhesion		
Uses	General Purpose		
Agency Ratings	MIL I-16923-B		
	MIL I-16923-C		
	MIL I-16923-D		
Processing Method	Casting		
	Potting		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	89		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	70.3	MPa	ASTM D638
Tensile Elongation (Break)	2.0 to 4.0	%	ASTM D638
Flexural Strength	117	MPa	ASTM D790
Compressive Strength	107	MPa	ASTM D695
Thermal	Nominal Value	Unit	
CLTE - Flow	4.0E-5	cm/cm/°C	
Thermal Conductivity	0.72	W/m/K	
Heat Deflection Temperature	155	°C	
Service Temperature	155	°C	
Linear Shrinkage	0.20	%	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+16	ohms · cm	ASTM D257
Dielectric Strength	17	kV/mm	ASTM D149
Dielectric Constant (1 kHz)	4.80		ASTM D150
Dissipation Factor (1 kHz)	0.020		ASTM D150
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			

Hardener	Mix Ratio by Weight: 9.0 to 10		
Resin	Mix Ratio by Weight: 100		
Shelf Life	52	wk	
Post Cure Time (150°C)	1.0	hr	
Uncured Properties	Nominal Value	Unit	Test Method
Color			
-- 1	Amber		
-- 2	Black		
Density			
-- 3	0.948	g/cm ³	
-- 4	1.59	g/cm ³	
Viscosity			ASTM D2393
-- 5	0.70	Pa·s	
-- 6	25	Pa·s	
-- 7	80	Pa·s	
Curing Time (100°C)	2.0	hr	
Pot Life (25°C)	150	min	
NOTE			
1.	INSULCURE 11B		
2.	INSULCAST 136		
3.	INSULCURE 11B		
4.	INSULCAST 136		
5.	INSULCURE 11B		
6.	Mixed		
7.	INSULCAST 136		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

