

Ebalta GM 984-2 / Comp. A+B

Polyurethane

Ebalta Kunststoff GmbH

Message:

This product is a polyurethane system.

GM 984-1 Comp. B (Amine) can be subject to colour variations due to raw materials, but these colour variations have no influence on the quality and the properties of the product.

The postcured material is not UV stable and darkens by and by. However according to our experience the change in colour does not affect its utilizability.

Physical final properties will be achieved after 7 days' curing at room temperature or after postcuring for 8 hrs. at 80°C.

As bonding agent on aluminium support we recommend our PU coupling paste KP 8.

Applications

Core boxes

fixtures

Properties

non-toxic according to regulations for hazardous material

very abrasion resistant

hard flexible

no brittleness phase

very well castable

Shore D hardness approx. 67

General Information			
Features	Semi Rigid		
	Good flexibility		
	Good wear resistance		
	Non-toxic		
Appearance	Orange		
Processing Method	Casting		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	65 - 69		ISO 7619
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	26.0 - 30.0	MPa	ISO 527-2
Tensile Strain (Break)	200 - 240	%	ISO 527-2
Flexural Modulus	785 - 865	MPa	ISO 178
Flexural Stress	30.0 - 32.0	MPa	ISO 178
Flexural Strain at Flexural Strength	6.5 - 7.5	%	ISO 178
Thermoset	Nominal Value	Unit	
Thermoset Components			
Resin	Mixing ratio by weight: 100		
Hardening method	Mixing ratio by weight: 130		
Additional Information			
Wear jet test : 40 W(V/t) [mm³/min] (internal tests)			
Uncured Properties	Nominal Value	Unit	
Density (20°C)	1.13 - 1.17	g/cm³	

Viscosity (25°C)	2.3 - 3.1	Pa·s
Curing Time (20°C)	12 - 16	hr
Pot Life ¹ (20°C)	17 - 20	min

NOTE

1. 200 g

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

