

Vandar® 4662Z

Polybutylene Terephthalate

Celanese Corporation

Message:

Vandar 4662Z is a high impact polyester alloy which contains 30% glass fiber loading. It is characterized by toughness, dimensional stability, and high modulus. Good weatherability and moldability are other key attributes.

General Information	
UL YellowCard	E45575-239399
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight
Features	Good dimensional stability
	Rigidity, high
	Impact resistance, high
	Good weather resistance
	Good toughness
RoHS Compliance	Contact manufacturer
Multi-Point Data	Isothermal Stress vs. Strain (ISO 11403-1)
	Shear Modulus vs. Temperature (ISO 11403-1)

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.47	g/cm ³	ASTM D792, ISO 1183
Melt Volume-Flow Rate (MVR) (250°C/5.0 kg)	5.50	cm ³ /10min	ISO 1133
Molding Shrinkage			
Flow	0.30 - 0.50	%	ASTM D955
Vertical flow direction	1.2 - 1.4	%	ISO 294-4
Flow direction	0.30 - 0.50	%	ISO 294-4
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	112		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7000	MPa	ISO 527-2/1A/1
Tensile Strength			
Yield, 23°C	82.7	MPa	ASTM D638
Fracture	80.0	MPa	ISO 527-2/1A/5
Tensile Elongation			
Fracture, 23°C	4.5	%	ASTM D638
Fracture	3.5	%	ISO 527-2/1A/5
Flexural Modulus (23°C)	6700	MPa	ISO 178

Flexural Stress (23°C)	130	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	10	kJ/m ²	ISO 179/1eA
23°C	20	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	70	kJ/m ²	ISO 179/1eU
23°C	70	kJ/m ²	ISO 179/1eU
Notched Izod Impact			ISO 180/1A
-30°C	10	kJ/m ²	ISO 180/1A
23°C	21	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	218	°C	ISO 75-2/B
0.45 MPa, annealed	214	°C	ASTM D648
1.8 MPa, not annealed	190	°C	ASTM D648
1.8 MPa, not annealed	175	°C	ISO 75-2/A
Glass Transition Temperature ¹	60.0	°C	ISO 11357-2
Vicat Softening Temperature	190	°C	ISO 306/B50
Melting Temperature ²	225	°C	ISO 11357-3, ASTM D3418
Linear thermal expansion coefficient			ISO 11359-2
Flow	1.5E-5	cm/cm/°C	ISO 11359-2
Lateral	1.3E-4	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+14	ohms	IEC 60093
Volume Resistivity			
--	1.0E+15	ohms · cm	ASTM D257
--	> 1.0E+14	ohms · cm	IEC 60093
Dielectric Strength	33	kV/mm	IEC 60243-1
Dielectric Constant			
1 kHz	3.90		ASTM D150
100 Hz	4.90		IEC 60250
1 MHz	4.30		IEC 60250
Dissipation Factor			
1 kHz	5.0E-3		ASTM D150
100 Hz	7.0E-3		IEC 60250
1 MHz	0.026		IEC 60250
Arc Resistance	120	sec	ASTM D495
Comparative Tracking Index	425	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	120 - 130	°C
Drying Time	4.0	hr
Suggested Max Moisture	0.020	%
Suggested Max Regrind	25	%
Hopper Temperature	20.0 - 50.0	°C
Rear Temperature	230 - 240	°C
Middle Temperature	235 - 250	°C
Front Temperature	235 - 250	°C
Nozzle Temperature	240 - 260	°C
Processing (Melt) Temp	235 - 260	°C
Mold Temperature	65.0 - 96.0	°C
Injection Rate	Moderate-Fast	
Back Pressure	0.00 - 0.345	MPa

Injection instructions

Manifold Temperature: 250 to 260°C Zone 4 Temperature: 240 to 260°C Feed Temperature: 230 to 240°C

NOTE

1. 10°C/min
2. 10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

