# Elvax® 760Q

## Ethylene Vinyl Acetate Copolymer

### **DuPont Packaging & Industrial Polymers**

#### Message:

DuPont<sup>™</sup> Elvax<sup>®</sup> 760Q is an ethylene-vinyl acetate copolymer resin for use in industrial applications. Composition 9.3 % By Weight Vinyl Acetate comonomer content Thermal Stabilizer: BHT antioxidant Features High level BHT antioxidant Applications

Elvax<sup>®</sup> resins can be used in a variety of applications involving molding, compounding, extrusion, adhesives, sealants, and wax blends. For additional information and properties associated with specific applications, please refer to the Grade Selector Guides found on the Elvax<sup>®</sup> website for industrial applications. http://www2.dupont.com/Elvax/en\_US/tech\_info/index.html

General Information					
Additive	Antioxidant				
	Heat Stabilizer				
Features	Antioxidant				
	Copolymer				
	Food Contact Acceptable				
	Heat Stabilized				
Uses	Adhesives				
	Blending				
	Compounding				
	Industrial Applications				
	Sealants				
	Wire Jacketing				
Agency Ratings	FDA 21 CFR 177.1350(a)(1)				
Forms	Pellets				
Processing Method	Blow Molding				
	Compounding				
	Compression Molding				
	Extrusion				
	Injection Molding				
	Sheet Extrusion				
	Structural Foam Molding				
Physical	Nominal Value	Unit	Test Method		
Specific Gravity	0.930	g/cm³	ASTM D792, ISO 1183		

Melt Mass-Flow Rate (MFR) (190°C/2.7 kg)	16 2.0	g/10 min	ASTM D1238, ISO 1133
Vinyl Acetate Content	9.3	wt%	
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	82.0	°C	ASTM D1525, ISO 306
Peak Melting Temperature	100	°C	ASTM D3418, ISO 3146
Injection	Nominal Value	Unit	
Processing (Melt) Temp	< 230	°C	
Extrusion	Nominal Value	Unit	
Melt Temperature	< 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

