

VESTOSINT® 1121 colored

Polyamide 12

Evonik Industries AG

Message:

VESTOSINT 1121 colored is a polyamide 12 powder suitable for all-purpose fluidized bed coating.

General Information			
Uses	Coating Applications		
Appearance	Unspecified Color		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density ¹ (23°C)	1.02	g/cm ³	ISO 1183
Apparent Density	> 0.44	g/cm ³	ISO 60
Water Absorption			ISO 62
Saturation, 100°C ²	1.9	%	
Saturation, 23°C ³	1.3	%	
Equilibrium, 23°C, 50% RH	0.50	%	
Particle Size Distribution			ISO 4610
< 32.0 µm ⁴	< 3.0	wt%	
< 100.0 µm	> 45.0	wt%	
< 250.0 µm	100.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75		ISO 868
Ball Indentation Hardness ⁵	90.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	43.0	MPa	ISO 527-2
Tensile Strain			ISO 527-2
Yield	6.0	%	
Break	> 100	%	
Taber Abrasion Resistance (100 Cycles, 500 g, CS-17 Wheel)	< 1.00	mg	ASTM D1242
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	176	°C	ISO 3146
CLTE - Flow (23 to 55°C)	1.1E-4	cm/cm/°C	ISO 11359-2
Specific Heat	2350	J/kg/°C	DIN 53765
Thermal Conductivity	0.23 to 0.29	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms · cm	IEC 60093
Electric Strength ⁶	90	kV/mm	IEC 60243-1
NOTE			

1.	Values from 300 µm foils of unpigmented VESTOSINT
2.	Immersion
3.	96%RH
4.	The value can reach 4% with effect colors
5.	H30
6.	K20/P50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

