

RTP 201 A FR

Polyamide 6

RTP Company

Message:

Glass Fiber - Flame Retardant

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Features	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.40 - 0.60	%	ASTM D955
Water Absorption (23°C, 24 hr)	1.5	%	ASTM D570
Moisture Content	0.20	%	
Primary Additive	10	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	116		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6210	MPa	ASTM D638
Tensile Strength	89.6	MPa	ASTM D638
Tensile Elongation (Yield)	3.0 - 5.0	%	ASTM D638
Flexural Modulus	5170	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	75	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	480	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	199	°C	ASTM D648
1.8 MPa, not annealed	182	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+14	ohms · cm	ASTM D257
Dielectric Strength ¹ (in Oil)	19	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.80		ASTM D150
Dissipation Factor (1 MHz)	0.017		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	V-0		UL 94

Injection	Nominal Value	Unit
Drying Temperature	82.2	°C
Drying Time	2.0	hr
Dew Point	-17.8	°C
Processing (Melt) Temp	243 - 279	°C
Mold Temperature	54.4 - 93.3	°C
Injection Pressure	68.9 - 103	MPa

Injection instructions

Desiccant Type Dryer Required.

NOTE

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

