

PERLEX® R3530

Polycarbonate

A. Schulman Europe

Message:

PERLEX® R3530 is a Polycarbonate (PC) material filled with 30% glass fiber. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of PERLEX® R3530 are:

Flame Rated

Flame Retardant

Typical application of PERLEX® R3530: Engineering/Industrial Parts

General Information			
UL YellowCard	E132739-100970623		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Flame Retardant		
Features	Flame Retardant		
Uses	Machine/Mechanical Parts		
Physical	Nominal Value	Unit	Test Method
Density	1.35	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	10	g/10 min	ISO 1133
Molding Shrinkage	0.30 to 0.50	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8400	MPa	ISO 527-2
Tensile Stress (Yield)	95.0	MPa	ISO 527-2
Flexural Modulus	8000	MPa	ISO 178
Flexural Stress	175	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	149	°C	ISO 75-2/B
1.8 MPa, Unannealed	143	°C	ISO 75-2/A
Vicat Softening Temperature	145	°C	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Ignition Temperature			IEC 60695-2-13
1.00 mm	850	°C	
2.00 mm	850	°C	
3.00 mm	850	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

