

Generic PMP - Glass Fiber

Polymethylpentene

Generic

Message:

This data represents typical values that have been calculated from all products classified as: Generic PMP - Glass Fiber
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Glass Fiber		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04 to 1.05	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus (23°C)	1720 to 7860	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53 to 86	J/m	ASTM D256
Unnotched Izod Impact (23°C)	160 to 170	J/m	ASTM D256

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

