

PALDUR® R 15 GF 30

Polybutylene Terephthalate

pal plast GmbH

Message:

PALDUR® R 15 GF 30 is a polybutene terephthalate (PBT) product, which contains a 30% glass fiber reinforced material. It can be processed by injection molding and is available in Europe. PALDUR® R 15 GF 30 applications include electrical/electronic applications, wire and cable, and automotive industries.

Features include:

flame retardant/rated flame

High stiffness

high strength

chemical resistance

Wear-resistant

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Rigidity, high		
	High strength		
	Good chemical resistance		
	Good wear resistance		
Uses	Electrical/Electronic Applications		
	Application in Automobile Field		
	Communication Equipment		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm ³	ISO 1183
Water Absorption			ISO 62
Saturated, 23°C	0.38	%	ISO 62
Equilibrium, 23°C, 50% RH	14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	9450	MPa	ISO 527-2/1A/1
Tensile Stress (Break, 23°C)	145	MPa	ISO 527-2/1A/5
Tensile Strain (Break, 23°C)	2.5	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	9.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	58	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	214	°C	ISO 306/B50
Melting Temperature (DSC)	225	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method

Comparative Tracking Index (Solution A)	350	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Additional Information			

Tensile Modulus, ISO 527, 23°C, 1 mm/min, Type A: 9000 to 9900 MPa Tensile Stress at Break, ISO 527, 23°C, 5 mm/min, Type A: 140 to 150 MPa Tensile Strain at Break, ISO 527, 23°C, 5 mm/min, Type A: 2 to 3 % Charpy Unnotched Impact, ISO 179, Type 1, Edgewise, 23°C: 50 to 65 kJ/m² Charpy Notched Impact, ISO 179, Type 1, Edgewise, Notch A, 23°C: 8 to 11 kJ/m² Vicat Softening Temperature, ISO 306, B50 (50°C/h 50N): 212 to 215 °C Density, ISO 1183: 1.53 to 1.55 g/cm³ Water Absorption, ISO 62, 23°C, Saturation: 0.35 to 0.4 % Moisture Absorption, ISO 62, 23°C, 50% RH: 0.12 to 0.15 %

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT