

Shin-Etsu RTV KE-3475TUV

Silicone Rubber, RTV-1

Shin-Etsu Silicones of America

Message:

Shin-Etsu RTV KE-3475TUV is a Silicone Rubber, RTV-1 material. This product is available in North America.

General Information		
Appearance	Clear/transparent	
Physical	Nominal Value	Unit
Specific Gravity	1.04	g/cm ³
Hardness	Nominal Value	Unit
Durometer Hardness (Shore A)	25	
Mechanical	Nominal Value	Unit
Shear Strength	0.414	MPa
Elastomers	Nominal Value	Unit
Tensile Strength	0.793	MPa
Thermal	Nominal Value	Unit
Thermal Conductivity	0.20	W/m/K
Electrical	Nominal Value	Unit
Dielectric Strength	22	kV/mm
Dissipation Factor (60 Hz)	1.0E-3	
Thermoset	Nominal Value	Unit
Tack Free Time	5.0	min
Additional Information		
One Component: YesProduct: NoAddition Cure: NoCondensation Cure: YesUL Listing: Yes		
Uncured Properties	Nominal Value	Unit
Viscosity	2.5	Pa · s
Curing Time ¹ (23°C)	72	hr
NOTE		
1.	50% RH	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT