

Polygen SC76C-BK

Polyphenylene Sulfide

Shanghai Polygen Science and Technology Co., Ltd.

Message:

glass/mineral filled PPS, lower cost, good strength, dimensional stability, excellent heat and chemical resistance

General Information			
Filler / Reinforcement	Glass \Mineral		
Features	Good dimensional stability		
	Good strength		
	Good chemical resistance		
	Heat resistance, high		
Appearance	Black		
Physical	Nominal Value	Unit	Test Method
Density	1.95	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Transverse flow	0.40	%	ISO 294-4
Flow	0.20	%	ISO 294-4
Water Absorption (Saturation, 23°C)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	140	MPa	ISO 527-2
Tensile Strain (Break)	1.2	%	ISO 527-2
Flexural Modulus	19000	MPa	ISO 178
Flexural Stress	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	7.0	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	265	°C	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	225	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	120 - 140	°C	
Drying Time	2.0 - 4.0	hr	
Processing (Melt) Temp	290 - 320	°C	
Mold Temperature	130 - 150	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

