

# HIDEN® F600

High Density Polyethylene

YUHW A Korea Petrochemical Ind. Co., Ltd.

Message:

HIDEN® F600 is a High Density Polyethylene material. It is available in Asia Pacific.

Important attributes of HIDEN® F600 are:

RoHS Compliant

Good Tear Strength

High Stiffness

Typical applications include:

Bags/Liners

Film

Food Contact Applications

Industrial Applications

General Information			
Features	Good Tear Strength		
	High Stiffness		
Uses	Bags		
	Film		
	General Purpose		
	Industrial Applications		
Agency Ratings	FDA Food Contact, Unspecified Rating		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density	0.957	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	0.035	g/10 min	ASTM D1238
Molding Shrinkage - Flow	1.5 to 2.5	%	Internal Method
Water Absorption (Equilibrium)	< 0.010	%	ASTM D570
Environmental Stress-Cracking Resistance <sup>1</sup>	> 1000	hr	ASTM D1693B
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	47		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	39.2	MPa	ASTM D638
Tensile Elongation (Break)	> 500	%	ASTM D638
Flexural Modulus	981	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	> 490	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load (1.8 MPa, Unannealed)	62.0	°C	ASTM D648
Brittleness Temperature	< -70.0	°C	ASTM D746
Vicat Softening Temperature	123	°C	ASTM D1525
Peak Melting Temperature	134	°C	ASTM D3418
NOTE			
1.	10%		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT