

# MIRASON™ 10P

Low Density Polyethylene

Mitsui Chemicals, Inc.

## Message:

MIRASON™ 10P is a Low Density Polyethylene material. It is available in Asia Pacific for extrusion coating. Primary attribute of MIRASON™ 10P: Good Processability.

Typical application of MIRASON™ 10P: Coating Applications

General Information			
Features	Good Processability		
Uses	Laminates		
Forms	Pellets		
Processing Method	Extrusion Coating		
Physical	Nominal Value	Unit	Test Method
Density	0.917	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.5	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	49		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
Yield	8.53	MPa	
Break	13.7	MPa	
Tensile Elongation (Break)	600	%	ASTM D638
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	85.0	°C	ASTM D1525
Melting Temperature	106	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT