

Wanthane® WHT-1190

Thermoplastic Polyurethane Elastomer (Polyester)

Wanhua Chemical Group Co., Ltd.

Message:

WHT-1190 is polyester-based TPU for injection molding and extrusion applications, supplied in form of transparent, translucent, colorless or slightly yellowish pellets with the characteristic of Plasticizer Free, Excellent strength , resilience and abrasion resistance

Applications:

Shoes, Seals, Hose, Cable, Conveyor Belt, Auto Part etc

General Information			
Features	Good Abrasion Resistance		
	Good Strength		
	Resilient		
Uses	Automotive Applications		
	Conveyor Parts		
	Footwear		
	Hose		
	Seals		
	Wire & Cable Applications		
Appearance	Colorless		
	Translucent		
	Transparent - Slight Yellow		
Forms	Pellets		
Processing Method	Extrusion		
	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.19	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	91		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ASTM D412
100% Strain	9.00	MPa	
300% Strain	20.0	MPa	
Tensile Strength	35.0	MPa	ASTM D412
Tensile Elongation (Break)	440	%	ASTM D412
Tear Strength	115	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method

Glass Transition Temperature	-33.0	°C	ASTM D3417
Injection	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	195	°C	
Middle Temperature	200	°C	
Front Temperature	205	°C	
Nozzle Temperature	210	°C	
Injection Pressure	70.0	MPa	
Extrusion	Nominal Value	Unit	
Drying Temperature	90.0 to 100	°C	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	195	°C	
Cylinder Zone 3 Temp.	200	°C	
Cylinder Zone 5 Temp.	205	°C	
Die Temperature	205	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

