

ESTOPLAST SR 4000GY01

Acrylonitrile Butadiene Styrene
Ester Industries Ltd.

Message:

Acrylonitrile Butadiene styrene - Unfilled, Flame retardant, Grey
Electrical & Electronic: Electrical Enclosure/ Housing/ Covers/ Fuse box

General Information			
Additive	demoulding		
	Flame retardancy		
Features	Halogenated		
	Good demoulding performance		
	Flame retardancy		
Uses	Electrical/Electronic Applications		
	Shell		
RoHS Compliance	RoHS compliance		
Appearance	Grey		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ASTM D1238
Water Absorption (Equilibrium, 23°C, 50% RH)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	35.0	MPa	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Strength	65.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	85.0	°C	ASTM D648
Flammability	Nominal Value	Test Method	
Flame Rating (3.2 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	80 - 90	°C	

Drying Time	3.0 - 4.0	hr
Rear Temperature	200 - 210	°C
Middle Temperature	220 - 230	°C
Nozzle Temperature	230 - 240	°C
Processing (Melt) Temp	230 - 240	°C
Mold Temperature	60 - 80	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

